

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 160 361 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.12.2001 Bulletin 2001/49

(51) Int Cl.7: C30B 25/02, C30B 29/36,
C30B 25/00

(21) Application number: 01113260.2

(22) Date of filing: 31.05.2001

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR
Designated Extension States:
AL LT LV MK RO SI

(72) Inventors:
• Nagasawa, Hiroyuki
Hachioji-shi, Tokyo 192-0373 (JP)
• Kawahara, Takamitsu
Kawasaki-shi, Kanagawa 213-0031 (JP)
• Yagi, Kuniaki
Oume-shi, Tokyo 198-0036 (JP)

(30) Priority: 31.05.2000 JP 2000162048

(71) Applicant: Hoya Corporation
Shinjuku-ku, Tokyo 161-0032 (JP)

(74) Representative: Leidescher, Thomas et al
Zimmermann & Partner,
Postfach 330 920
80069 München (DE)

(54) Method of manufacturing silicon carbide, silicon carbide, composite material, and semiconductor element

(57) To provide a method of manufacturing silicon carbide by forming silicon carbide on a substrate surface from an atmosphere containing a silicon carbide feed-stock gas comprising at least a silicon source gas and a carbon source gas under condition 1 or 2 below:


Condition 1: the partial pressure p_s of silicon source gas is constant (with $p_s > 0$), the partial pressure of carbon source gas consists of a state p_{c1} and a state p_{c2} that are repeated in alternating fashion, wherein p_{c1} and p_{c2} denote partial pressures of carbon source gas, $p_{c1} > p_{c2}$, and p_{c1}/p_s falls within a

range of 1-10 times the attachment coefficient ratio (S_s/S_c), p_{c2}/p_s falls within a range of less than one time S_s/S_c ;

Condition 2: the partial pressure p_c of carbon source gas is constant (with $p_c > 0$), the partial pressure of silicon source gas consists of a state p_{s1} and a state p_{s2} that are repeated in alternating fashion, wherein p_{s1} and p_{s2} denote partial pressures of silicon source gas, $p_{s1} < p_{s2}$, and p_c/p_{s1} falls within a range of 1-10 times S_s/S_c , p_c/p_{s2} falls within a range of less than one time S_s/S_c .

Fig. 1

Condition 1



Description**Field of the Invention**

5 [0001] The present invention relates to methods of manufacturing silicon carbide (for example, thin films and ingots) employed as a substrate material in semiconductor devices and X-ray masks, chiefly silicon carbide employed in the components of semiconductor manufacturing devices, dummy wafers employed in semiconductor element manufacturing steps, and silicon carbide structural members (for example, heaters, anticorrosion products (screws, bearings), and the like).

Related Art

10 [0002] Silicon carbide is a semiconductor with a broad forbidden bandwidth of 2.2 eV or greater and is a thermally, chemically, and mechanically stable crystal. Further, due to high thermal conductivity, its application as a semiconductor material under conditions of high frequency, high power, high temperature, and the like is anticipated.

15 [0003] Methods of manufacturing silicon carbide include reacting coke and silicon on a heated carbon surface and precipitating silicon carbide on a carbon surface (the Atchison method); heating and sublimating silicon carbide formed by the Atchison method and recrystallizing it (sublimation method, improved Reilly method); the liquid deposition method in which silicon is melted in a carbon crucible and the suspended carbon and silicon are reacted in the crucible while drawing the product upward; and the like.

20 [0004] Methods employed to obtain high purity silicon carbide films with few planar defects include chemical vapor deposition (CVD) in which a carbon source gas and a silicon source gas are thermally reacted at ordinary pressure or under a reduced pressure atmosphere and precipitated onto a substrate surface; and atomic layer epitaxy (ALE) in which a silicon source and a carbon source are alternately adsorbed onto a substrate surface, and epitaxially growing silicon carbide while extending the crystalline properties of the substrate.

25 [0005] Although the Atchison method produces inexpensive, large quantities of silicon carbide, the precipitating silicon carbide is amorphous, comprising crystalline polymorphism and large quantities of impurities. In particular, this method cannot be employed to manufacture semiconductor materials in which defects and impurities are problematic.

30 [0006] The improved Reilly method reduces the problems of crystalline polymorphism, amorphism, and the like associated with the Atchison method. However, it is difficult to reduce the impurities incorporated into the crystal, and increasing the area of the crystal and decreasing the number of defects are no simple tasks.

35 [0007] The method that is generally employed to reduce the crystal defects and impurities that are problematic in the improved Reilly method is to use CVD or ALE to epitaxially grow silicon carbide while reducing the defect density and impurities on a silicon carbide substrate obtained by the improved Reilly method. However, since the area of the crystals obtained by these methods is limited to the area of the silicon carbide obtained by the improved Reilly method, large-area, high-quality silicon carbide cannot be obtained.

40 [0008] To increase the area of silicon carbide, the general method has been devised of using CVD or ALE to heteroepitaxially grow a silicon carbide layer on a single crystal silicon substrate employed as a semiconductor material. However, high concentrations of defects are produced at the interface of the silicon substrate and the silicon carbide. Thus, the quality of the crystal is poorer than that of epitaxially grown silicon carbide layers formed on silicon carbide substrates obtained by the improved Reilly method. When employing heteroepitaxial growth, crystal quality can be improved by increasing the thickness of the film of silicon carbide being grown. However, since the rate of silicon carbide growth by CVD or ALE is extremely low, the application of silicon carbide obtained by heteroepitaxial growth is currently impeded.

45 [0009] The rate of growth of silicon carbide can be increased to some extent by increasing the partial pressure of the starting gasses using CVD. However, the faster the growth rate, the more crystal defects tend to increase in the silicon carbide. Since the ALE method requires that a certain quantity of atoms or molecules be uniformly adsorbed to the substrate surface under thermal equilibrium, increasing the growth rate of silicon carbide by increasing the amount of gas being fed as is done in CVD is undesirable.

50 [0010] It is therefore the object of the present invention to provide an improved method for the production of silicon carbide and improved silicon carbide products. This object is solved by the methods of independent claims 1, 7 and 12, the silicon carbide block of independent claim 9 and the semiconductor element according to independent claim 11. Further advantageous features, aspects and details of the invention are evident from the dependent claims, the description, the examples, embodiments, and the drawings.

55 [0011] According to one aspect, the present invention provides a method of manufacturing silicon carbide affording adequate ease of production by increasing the growth rate of silicon carbide in gas vapor growth without increasing crystal defects.

[0012] According to a further aspect, the present invention provides a method of manufacturing silicon carbide of a

quality suitable for use as a semiconductor element material with fewer crystal defects and affording adequate ease of production even in heteroepitaxial growth employing a substrate other than silicon carbide. A further object of the manufacturing method of the present invention is to obtain silicon carbide not just as a thin film, but also as an ingot or structural member.

5 **[0013]** According to a still further aspect, the present invention provides silicon carbide (not just thin films, but also ingots and structural members) having heretofore unseen dimensions (bores) in the form of silicon carbide of a quality suitable for use as a semiconductor element material with reduced crystal defects.

[0014] According to yet another aspect, the present invention provides a semiconductor element employing the above-described silicon carbide as a substrate, and to provide a method of manufacturing composite materials employing the above-described silicon carbide as seed crystal.

10 **[0015]** The aforementioned objects can be achieved by the present invention as follows.

[0016] In accordance with the present invention, there is provided a method of manufacturing silicon carbide by forming silicon carbide from an atmosphere containing a silicon carbide feedstock gas on a substrate surface, characterized in that:

15 said silicon carbide feedstock gas comprises at least a silicon source gas and a carbon source gas;

the partial pressure p_s of said silicon source gas in said atmosphere is constant (with $p_s > 0$), the partial pressure of said carbon source gas in said atmosphere consists of a state p_{c1} and a state p_{c2} that are repeated in alternating fashion (referred to as condition 1 below);

(where p_{c1} and p_{c2} denote partial pressures of said carbon source gas, $p_{c1} > p_{c2}$, and the partial pressure ratio (p_{c1}/p_s) falls within a range of 1-10 times the attachment coefficient ratio (S_s/S_c), the partial pressure ratio (p_{c2}/p_s) falls within a range of less than one time the attachment coefficient ratio (S_s/S_c))

(where S_s denotes the attachment coefficient of silicon source gas to the silicon carbide substrate at the substrate temperature during formation of said silicon carbide, and S_c denotes the attachment coefficient of carbon source gas to the silicon carbide substrate at the substrate temperature during the forming of said silicon carbide))

25 or

the partial pressure p_c of said carbon source gas in said atmosphere is constant (with $p_c > 0$), the partial pressure of said silicon source gas in said atmosphere consists of a state p_{s1} and a state p_{s2} that are repeated in alternating fashion (referred to as condition 2 below);

(where p_s and p_{s2} denote partial pressures of said silicon source gas, $p_{s1} < p_{s2}$, and the partial pressure ratio (p_c/p_{s1}) falls within a range of 1-10 times the attachment coefficient ratio (S_s/S_c), the partial pressure ratio (p_c/p_{s2}) falls within a range of less than one time the attachment coefficient ratio (S_s/S_c))

(where S_s denotes the attachment coefficient of silicon source gas to the silicon carbide substrate at the substrate temperature during formation of said silicon carbide, and S_c denotes the attachment coefficient of carbon source gas to the silicon carbide substrate at the substrate temperature during the forming of said silicon carbide)).

35 **[0017]** In the above manufacturing method of silicon carbide, the following conditions are preferred.

[0018] In condition 1, p_{c1} and p_{c2} each continue for a prescribed period, and in condition 2, p_{s1} and p_{s2} each continue for a prescribed period.

[0019] Silicon carbide is formed on a substrate the temperature of which is not less than 900°C.

40 **[0020]** The above silicon source gas is at least one member selected from the group consisting of SiH_4 , Si_2H_6 , SiCl_4 , SiHCl_3 , SiH_2Cl_2 , $\text{Si}(\text{CH}_3)_4$, $\text{SiH}_2(\text{CH}_3)_2$, $\text{SiH}(\text{CH}_3)_3$, and $\text{Si}_2(\text{CH}_3)_6$, and/or said carbon source gas is at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_2 , C_2H_4 , CCl_4 , CHF_3 , and CF_4 .

[0021] p_{c2} or p_{s1} is essentially 0.

[0022] p_{c2} is essentially 0, the time during which the partial pressure of the carbon source gas is set to p_{c1} is 0.1-30 seconds, and the time during which the partial pressure of the carbon source gas is set to p_{c2} is 0.1-30 seconds.

45 **[0023]** The present invention further relates to a method of manufacturing silicon carbide characterized in that the silicon carbide manufactured in any of claims 1-6 is employed as seed crystal and in that silicon carbide is formed on said seed crystal by vapor phase epitaxy, sublimation recrystallization, or liquid deposition.

[0024] In the above manufacturing method of silicon carbide, the preferred is that silicon carbide blocks 10.16 - 15.24 cm (4-6 inches) in bore are formed by vapor phase epitaxy, sublimation recrystallization, or liquid deposition.

50 **[0025]** The present invention further relates to a silicon carbide block characterized by having a bore of 10.16 - 15.24 cm (4-6 inches).

[0026] In the above silicon carbide block, the preferred is that the planar defect density is not more than $10^3/\text{cm}^2$.

[0027] The present invention further relates to a semiconductor element employing as substrate the silicon carbide block described above.

55 **[0028]** The present invention further relates to a method of manufacturing composite materials characterized in that silicon carbide manufactured by the above-mentioned method is employed as seed crystal and diamond and/or gallium nitride is formed on said seed crystal.

Brief Description of the Drawings

[0029]

5 Fig. 1 is an example of the cycle of condition 1 of the present invention.

Fig. 2 is an example of the cycle of condition 2 of the present invention.

10 Fig. 3 is a type drawing descriptive of the operation of the present invention: (1) shows how the silicon source is fed onto the substrate, (2) shows how the silicon source fed onto the substrate forms an epitaxial growth layer of silicon, (3) shows how the epitaxial growth layer of silicon formed on the substrate reacts with the carbon source to form silicon carbide, and (4) shows how the carbon source forms an adsorption layer on the silicon carbide layer, impeding adsorption of the silicon source.

15 Fig. 4 is the method of supplying feedstock gas in Comparative Example 1.

Fig. 5 is the method of supplying feedstock gas in Embodiment 1.

20 Fig. 6 is the method of supplying feedstock gas in Embodiment 2.

Fig. 7 is the method of supplying feedstock gas in Embodiment 3.

Fig. 8 is the method of supplying feedstock gas in Embodiment 4.

25 Fig. 9 is the method of supplying feedstock gas in Embodiment 5.

Fig. 10 is a schematic drawing of the method used to measure the attachment coefficient ratio.

30 Fig. 11 is a graph showing the change over time of the quantity of gas that is fed.

Fig. 12 is a graph showing the change over time of the number $n(t)$ (relative value) of gas molecules desorbing from the substrate surface as measured by quadrupole mass spectrometry.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

35

[0030] The method of manufacturing silicon carbide of the present invention is chiefly a method of manufacturing thin films of silicon carbide on a substrate surface from an atmosphere containing silicon carbide feedstock gases. However, it is not limited to thin films of silicon carbide, and can be used to manufacture silicon carbide ingots and structural members of silicon carbide.

40 [0031] The method of manufacturing silicon carbide of the present invention is characterized by conditions 1 and 2 below.

[0032] Condition 1: The silicon carbide feedstock gas comprises at least a silicon source gas and a carbon source gas. The partial pressure p_s of the silicon source gas in the atmosphere is constant (with $p_s > 0$), and the partial pressure of the carbon source gas repeatedly alternates between a state pc_1 and a state pc_2 .

45 [0033] Condition 2: The silicon carbide feedstock gas comprises at least a silicon source gas and a carbon source gas. The partial pressure pc of the carbon source gas is constant (with $pc > 0$), and the partial pressure of the silicon source gas repeatedly alternates between a state p_s and a state p_{s2} .

[0034] Fig. 1 shows an example of the cycle of condition 1.

50 [0035] In condition 1, the partial pressure p_s of the silicon source gas is constant in the atmosphere. However, $p_s > 0$. The partial pressure of the carbon source gas in the atmosphere repeatedly alternates between a state pc_1 and a state pc_2 . That is, since $pc_1 > pc_2$, the partial pressure of the carbon source gas is increased. Although $pc_1 > pc_2$, pc_2 can essentially be 0. What is meant in the present Specification by the partial pressure being essentially 0 is not greater than 10^{-5} Torr. The time (tc_1) during which the pressure of the carbon source gas is made pc_1 and the time (tc_2) during which the partial pressure of the carbon source gas is made pc_2 are repeatedly alternated.

55 [0036] In condition 1, during time tc_2 when the partial pressure of the carbon source gas is made pc_2 , the partial pressure of the carbon source gas is lower than the silicon source gas, and so long as pc_2 is not zero, silicon carbide precipitates. However, Si also precipitates in this state. Subsequently, during time tc_1 when the partial pressure of the carbon source gas is pc_1 , the partial pressure of the carbon source gas becomes relatively high, and simultaneously

with the precipitation of silicon carbide, Si reacts with C supplied by the silicon source gas, creating silicon carbide. To permit the creation of such states, t_{c1} and t_{c2} , p_s , p_{c1} and p_{c2} , the type of silicon source gas and carbon source gas, the substrate temperature, the capacity of the reaction vessel, and the like are considered and suitably determined. For example, t_{c1} can be set to within a range of 0.1-60 sec and t_{c2} to within a range of 0.1-90 sec. Setting p_{c2} to 0; setting time t_{c1} , when the partial pressure of the carbon gas is set to p_{c1} , to 0.1-30 sec; and setting time t_{c2} , when the partial pressure of the carbon source gas is set to p_{c2} , to 0.1-30 sec is particularly desirable from the viewpoint of decreasing crystal defects in the silicon carbide and increasing the growth rate.

[0037] Further, in condition 1, the partial pressure ratio (p_{c1}/p_s) is set to within a range of 1-10 times the attachment coefficient ratio (S_s/S_c) and the partial gas ratio (p_{c2}/p_s) is set to within a range of less than one time the attachment coefficient ratio (S_s/S_c). Thus, during time t_{c2} when the partial pressure of the carbon source gas is p_{c2} , silicon carbide and Si precipitate simultaneously, and subsequently, during time t_{c1} when the partial pressure of the carbon source gas is p_{c1} , the precipitation of silicon carbide and the formation of silicon carbide through the reaction of precipitated Si and C occur simultaneously. The attachment coefficient ratio (S_s/S_c) can be calculated by a method described further below.

[0038] An example of the cycle of condition 2 is shown in Fig. 2.

[0039] In condition 2, the partial pressure p_c of the carbon source gas in the atmosphere is held constant. However, $p_c > 0$. The state where the partial pressure of the silicon source gas in the atmosphere is p_s1 and the state in which it is p_s2 are repeatedly alternated. That is, since $p_s1 < p_s2$, the partial pressure of the silicon source gas is increased. Although $p_s1 < p_s2$, p_s1 can be essentially 0. The time (t_{s1}) during which the partial pressure of the silicon source gas is made p_s1 and the time (t_{s2}) during which the partial pressure of the silicon gas source is made p_s2 are repeatedly alternated.

[0040] In condition 2, during time t_{s2} when the partial pressure of the silicon source gas is made p_s2 , the partial pressure of the carbon source gas is lower than that of the silicon source gas and silicon carbide precipitates, but Si also precipitates during that state. Subsequently, during time t_{s1} when the partial pressure of the silicon source gas is made p_s1 , the partial pressure of the silicon source gas becomes relatively low, and Si reacts with C supplied by the carbon source gas to form silicon carbide simultaneously with the precipitation of silicon carbide. To permit the creation of such states, t_{s1} and t_{s2} , p_c , p_s1 and p_s2 , the type of silicon source gas and carbon source gas, the substrate temperature, the capacity of the reaction vessel, and the like are considered and suitably determined. For example, t_{s1} can be set to within a range of 0.1-60 sec and t_{s2} to within a range of 0.1-60 sec.

[0041] Further, in condition 2, partial pressure ratio (p_c/p_{s1}) is set to within a range of 1-10 times the attachment coefficient ratio (S_s/S_c), and partial pressure ratio (p_c/p_{s2}) is set to within a range of less than one time attachment coefficient ratio (S_s/S_c). Thus, during time t_{s2} when the partial pressure of the silicon source gas is p_s2 , precipitation of silicon carbide and Si occurs simultaneously, and subsequently, during time t_{s1} when the partial pressure of the silicon source gas is p_s1 , precipitation of silicon carbide and the formation of silicon carbide through the reaction of precipitated Si and C occur simultaneously.

[0042] Attachment coefficient ratio (S_s/S_c) can be determined in the following manner.

[0043] A valve is used to blow a pulse of either the carbon source gas or the silicon source gas onto the surface of the silicon carbide substrate. The temperature of the silicon carbide substrate is preset to the substrate temperature for forming silicon carbide.

[0044] The partial pressure at $T=0$ is instantaneously raised to a fixed level.

[0045] Gas molecules temporarily attached to the surface of the substrate are desorbed, but the quantity (a relative value) of the gas molecules that are desorbed is monitored with a quadrupole mass spectrometer. A collimator is positioned between the substrate and the quadrupole mass spectrometer so that in this process, just the gas molecules that are desorbed from the substrate enter the mass spectrometer. (Fig. 10 is a schematic of the measurement system.)

[0046] The graph of Fig. 11 shows the change over time of the level of gas supply. The graph of Fig. 12 shows the change over time in the quantity $n(t)$ (relative value) of gas molecules desorbed from the surface of the substrate being measured by the quadrupole mass spectrometer.

[0047] Let τ denote the time coordinates of the point of intersection of the tangent of $n(t)$ when $t=0$ and the asymptotic line when $\tau \rightarrow \infty$. Let τ_c (the average residence time of the carbon source gas on the surface of the substrate) denote τ when the gas employed is the carbon source gas. Let τ_s (the average residence time of the silicon source gas on the surface of the substrate) denote τ when the gas employed is the silicon source gas. The attachment coefficient ratio can then be calculated from the relation $S_c/S_s = \tau_c/\tau_s$.

[0048] During the formation of silicon carbide by the manufacturing method of the present invention, setting the substrate temperature to not less than 900°C promotes the decomposition of molecules adhering to the substrate surface and promotes the reaction, and is suitable from the viewpoint of making it possible to establish a prescribed relation (the relation specified by condition 1 and condition 2) between the partial pressure ratio and the attachment coefficient ratio that is independent of the types of gas. The substrate temperature desirable falls with a range of 1,100-1,370°C.

[0049] Examples of substrates suitable for use in forming silicon carbide are Si, SiC, TiC, sapphire, and diamond.

[0050] The operation of the manufacturing method of the present invention will be described based on Fig. 3. Fig. 3 describes the case of condition 1.

[0051] As shown by Fig. 3 (1), when a silicon source is continuously fed to the substrate surface ($p_s = \text{constant}$, $p_{c2} = 0$), the silicon source thermally decomposes, for example, on the surface of the substrate that has been heated to not less than 900°C and a single crystal of silicon forms on the substrate surface (Fig. 3(2)). Here, when the carbon source is temporarily supplied (at p_{c2}), the formation of the silicon layer on the substrate surface is inhibited and the silicon layer that formed on the substrate surface prior to the introduction of the carbon source simultaneously reacts with the carbon source, forming silicon carbide (Fig. 3(3)). In this process, when the partial pressure of the carbon source has been set to p_{c2} , the attachment coefficient of the carbon source to S_c , the partial pressure of the silicon source to p_s , and the attachment coefficient of the silicon source to S_s , and when p_{c2} or p_s is controlled to maintain a relation where p_{c2}/p_s during the carbon source supply is not less than one time and not more than ten times S_s/S_c , the incorporation of the silicon source onto the substrate surface is inhibited during feeding of the carbon source (Fig. 3(4)).

[0052] When the carbon source is fed intermittently as set forth above, the process of silicon layer epitaxial growth on the substrate surface and process of the formation of silicon carbide through the reaction of the silicon layer that has been epitaxially grown and the carbon source are completely separated in time, yielding single-crystal silicon carbide with few defects. Further, since the carbon source adsorption layer is segregated in the vicinity of the substrate surface during feeding of the carbon source in the present invention and the silicon source remains, as soon as feeding of the carbon source is stopped, the silicon layer grows epitaxially and the growth rate of the silicon carbide increases. However, when p_{c2}/p_s falls below S_s/S_c , the silicon source is incorporated into the substrate surface even during feeding of the carbon source, yielding silicon carbide in which there is a shift in crystal orientation with the underlayer, or microcrystals of silicon are picked up in the silicon carbide, precluding the effect of the present invention. To achieve adequate mass production (growth rate of silicon carbide) based on the present invention, the time during which the carbon source is fed per cycle is preferably not more than 30 sec. However, at less than 0.1 sec, it is difficult to supply an adequate carbon source. The interval of the intermittent supply of carbon source is desirably not less than 0.1 sec to desorb the carbon source that has adsorbed onto the substrate surface and to promote the growth of silicon on the substrate surface. However, at greater than 30 sec, the growth rate of the silicon carbide tends to be compromised.

[0053] Mechanism of deposition of silicon carbide and the like in condition 1 has been described above; that of condition 2 is substantially identical therewith.

[0054] Although the silicon source gas and the carbon source gas employed in the manufacturing method of the present method are not specifically limited, at least one member from among the group consisting of SiH_4 , Si_2H_6 , SiCl_4 , SiHCl_3 , SiH_2Cl_2 , $\text{Si}(\text{CH}_3)_4$, $\text{SiH}_2(\text{CH}_3)_2$, $\text{SiH}(\text{CH}_3)_3$, and $\text{Si}_2(\text{CH}_3)_6$ can be employed as the silicon source gas, for example. Further, at least one member from among the group consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_2 , C_2H_4 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source gas, for example.

[0055] Based on the method of manufacturing silicon carbide of the present invention as set forth above, large-bore silicon carbide with few (or no) crystal defects can be manufactured with good ease of production. In particular, even when the substrate is something other than silicon carbide - single crystal silicon, for example - it is possible to manufacture large-bore silicon carbide with few (or no) crystal defects with good ease of production.

[0056] The present invention covers methods of manufacturing silicon carbide characterized in that silicon carbide manufactured by the above-described manufacturing method of the present invention, particularly thin film silicon carbide, is employed as seed crystal, and silicon carbide is formed on this seed crystal by vapor phase epitaxy, sublimation recrystallization, or liquid deposition.

[0057] Vapor phase epitaxy, sublimation recrystallization, and liquid deposition methods for forming silicon carbide are as follows.

[0058] In vapor phase epitaxy methods of forming silicon carbide, at least two types of gas consisting of a carbon source and a silicon source, or at least one type of gas comprising both carbon and silicon, is thermally decomposed in a vapor phase or on the surface of the substrate and reacted, yielding silicon carbide on the substrate surface. For example, an SiC substrate based on the present invention is employed as seed crystal, and while being heated under vacuum to 1,200°C, 1 sccm of silane gas and 0.5 sccm of propane gas are introduced, and 1 slm of a noble gas in the form of Ar is fed. While maintaining the pressure of the reaction system at 13.3 Pa (100 mTorr), SiC is grown again on the seed crystal SiC substrate.

[0059] In sublimation recrystallization methods of forming silicon carbide, silicon carbide feedstock is charged to a graphite crucible, a seed crystal of the silicon carbide of the present invention is introduced opposite the feedstock, and while controlling the temperature of the feedstock to be somewhat higher than that of the seed crystal, the crucible is heated to not less than 2,000°C at one atmospheric pressure, causing the feedstock to sublime and recrystallize on the seed crystal.

[0060] In liquid deposition methods of forming silicon carbide, Si is melted in a carbon crucible heated to 1,500°C,

the surface of the silicon carbide (seed crystal) of the present invention is contacted with the liquid surface, and silicon carbide grows on the seed crystal from molten Si and suspended carbon in the molten Si.

[0061] Silicon carbide blocks (for example, ingots and structural members) with bores of 4-6 inches (ranging from 100-160 mm) can be formed by the above-described manufacturing methods (vapor phase epitaxy, sublimation re-crystallization, and liquid deposition). Here, the term "bore" corresponds to the diameter of the substrate employed in the above-described manufacturing methods. In conventional silicon carbide blocks, the bore runs up to about three inches, but based on the manufacturing method of the present invention, silicon carbide blocks with bores of 4-6 inches (equivalent to 102-152 mm, ranging from 100-160 mm) can be obtained. Further, the blocks obtained have planar defect densities of not more than $10^3/\text{cm}^2$.

[0062] Accordingly, the present invention covers silicon carbide blocks characterized by bores of 10.16 - 15.24 cm (4-6 inches). These silicon carbide blocks also have planar defect densities of not more than $10^3/\text{cm}^2$.

[0063] The present invention further covers semiconductor elements employing the above-described silicon carbide blocks of the present invention as substrates. Examples of such semiconductor elements are Schottky diodes, blue light-emitting diodes, and other power devices and light-emitting elements.

[0064] Further, these semiconductor elements can also be manufactured by methods of manufacturing composite materials including the formation of diamond and/or gallium nitride on seed crystals of silicon carbide manufactured by the above-described manufacturing method of the present invention, for example.

[0065] Diamond can be formed on the seed crystal in the following manner.

[0066] A seed crystal is placed in a vacuum chamber and heated to 500°C , after which propane gas is introduced into the vacuum chamber. The pressure within the chamber is then regulated to 1.33 Pa (10 mTorr) with an evacuation system. Next, a high frequency

[0067] of 13.56 MHz (200 W) is applied between the seed crystal and a flat electrode facing the seed crystal and a plasma is formed. The carbon decomposed by the plasma is deposited on the seed crystal and remains at the correct crystal position to form diamond on the seed crystal.

[0068] Further, the formation of gallium nitride on seed crystal can be performed as follows.

[0069] A silicon carbide (seed crystal) substrate obtained by the manufacturing method of the present invention is placed in a vacuum vessel and heated to 1040°C . Next, 10 slm of ammonia and 0.5 sccm of trimethylgallium are introduced into the reaction vessel, and while the various gases decompose on the seed crystal, a GaN forming reaction takes place at correct crystal position.

[0070] The present disclosure relates to the subject matter contained in Japanese Patent Application No. 2000-162048 filed on May 31, 2000, which is expressly incorporated herein by reference in its entirety.

[Embodiments]

[0071] Embodiments of the present invention are described below.

[0072] In the embodiments and comparative examples, the partial pressures of the silicon source gas and carbon source gas are proportional to the feed flow rates. Thus, the partial pressure ratio is equal to the flow rate ratio.

Comparative Example 1 (intermittent feeding of both silicon source and carbon source)

[0073] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of $1,200^\circ\text{C}$, and cubic silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of Ar to a pressure of 100 mTorr during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiH_2Cl_2 and C_2H_2 . The ratio Ss/Sc of the attachment coefficients of SiH_2Cl_2 and C_2H_2 on the surface of the silicon carbide was 0.25.

[0074] A comparative example will be given next based on Fig. 4. Silicon carbide was grown by feeding SiH_2Cl_2 and C_2H_2 at separate times. SiH_2Cl_2 feeding was conducted continuously for 5 sec at a partial pressure of 10 sccm. Next, after stopping the feeding of gases other than Ar, C_2H_2 was fed for 5 sec.

[0075] After feeding C_2H_2 for 5 sec, the feeding of gases other than Ar was stopped, and SiH_2Cl_2 feeding was begun. This alternating feeding of gases was repeated 1,000 times, yielding a cubic silicon carbide film on the silicon substrate. Growing the silicon carbide took 5.56 hr. As a result of the growth, a $0.8\text{ }\mu\text{m}$ single crystal of silicon carbide was obtained on the silicon substrate. As a result, the growth rate of the silicon carbide was $0.144\text{ }\mu\text{m/hr}$. However, surface defects such as anti phase boundaries and twin crystal bands were present on the surface of the silicon carbide at a density of $10^3/\text{cm}^2$.

Embodiment 1 (continuous feeding of silicon source, intermittent feeding of carbon source)

[0076] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of 1,200°C, and 3C-silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of Ar to a pressure of 100 mTorr during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiH_2Cl_2 and C_2H_2 . The ratio S_s/S_c of the attachment coefficients of SiH_2Cl_2 and C_2H_2 on the surface of the silicon carbide was 0.25.

[0077] The embodiment of the present invention will be described based on Fig. 5.

While continuously feeding SiH_2Cl_2 at a partial pressure of 10 sccm, C_2H_2 was intermittently fed to grow silicon carbide. The partial pressure of the SiH_2Cl_2 was 10 sccm. C_2H_2 was intermittently fed 1,000 times at intervals of 5 sec at a partial pressure of 10 sccm. Each time, the C_2H_2 was fed for 5 sec. Growth of silicon carbide required 2.8 hr. As a result of the growth, 67 μm of single crystal silicon carbide was obtained on the silicon substrate. The effective growth rate of silicon carbide was 24 $\mu\text{m/hr}$. Further, surface defects such as anti phase boundaries and twin crystal bands had been eliminated from the surface of the crystal obtained. In this manner, the use of the present invention permitted an accelerated rate of silicon carbide growth exceeding 10 $\mu\text{m/hr}$ and permitted a substantial decrease in crystal defects. ($fc_2/fs=4xS_s/S_c$, $fc_1=0$, that is $pc_2/ps=4xS_s/S_c$, $pc_1=0$).

[0078] Although a cold wall CVD device was employed in the present embodiment, a hot wall type CVD device may also be employed to achieve results identical to those of the present embodiment.

[0079] Further, although the silicon {001} plane was employed as substrate, the same rapid growth and crystal properties as in the present embodiment can be achieved using the silicon {111} plane, cubic silicon carbide {001} plane, cubic silicon carbide {111} plane, cubic silicon carbide $\{-1,-1,-1\}$ plane, hexagonal silicon carbide $\{1,1,-2,0\}$ plane, hexagonal silicon carbide $\{0,0,0,1\}$ plane, hexagonal silicon carbide $\{0,0,0,-1\}$ plane, and hexagonal silicon carbide $\{1,-10,0\}$ plane.

[0080] Although C_2H_2 was employed as the carbon source and SiH_2Cl_2 as the silicon source in the present embodiment, so long as the partial pressure ratio (flow rate ratio) of the carbon source to the silicon source is not less than one time and not more than ten times the attachment coefficient ratio, at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_6 , C_2H_4 , C_2H_2 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source, and at least one member selected from the group consisting of SiH_4 , Si_2H_6 , SiCl_4 , SiHCl_3 , $\text{Si}(\text{CH}_3)_4$, $\text{SiH}_2(\text{CH}_3)_2$, $\text{SiH}(\text{CH}_3)_3$, and $\text{Si}_2(\text{CH}_3)_6$ can be employed as the silicon source to achieve the effect of the present invention.

Embodiment 2 (continuous supply of silicon, intermittent supply of carbon)

[0081] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of 1,200°C, and 3C-silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of Ar to a pressure of 13.3 Pa (100 mTorr) during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiH_2Cl_2 and C_2H_2 . The ratio S_s/S_c of the attachment coefficients of SiH_2Cl_2 and C_2H_2 on the surface of the silicon carbide was 0.25.

[0082] The embodiment of the present invention will be described based on Fig. 6 below.

While continuously feeding SiH_2Cl_2 at a flow rate of 10 sccm, C_2H_2 was intermittently fed to grow silicon carbide. The SiH_2Cl_2 flow rate was a constant 10 sccm. C_2H_2 was intermittently fed 1,000 times at intervals of 5 sec. Each time, C_2H_2 was fed for 5 sec. However, the flow rate fc of C_2H_2 was treated as a parameter and fc_2 was varied from 0.5-200 sccm and the change in silicon carbide growth rate was observed. ($fc_2/fs=4xS_s/S_c$, $fc_1=0$, that is $pc_2/ps=4xS_s/S_c$, $pc_1=0$).

[0083] Table 1 shows the changes in growth rates of silicon carbide by fc_2 . When fc_2/fs (that is, pc_2/ps) was S_s/S_c (0.25) or greater, the growth rate of silicon carbide exceeded 10 $\mu\text{m/hr}$ and the effect of the present invention was apparent. However, when fc_2/fs (that is, pc_2/ps) was less than S_s/S_c (0.25), not only did the growth rate of silicon carbide decrease, but silicon precipitated in the silicon carbide, precluding the effect of the present invention. Further, when fc_2/fs (that is, pc_2/ps) exceeded 2.5, the level of adsorption of C_2H_2 on the substrate surface increased. Since adsorption of SiH_2Cl_2 was blocked, the growth rate of silicon carbide dropped precipitously, precluding the effect of the present invention. Silicon carbide grown at an fc_2/fs of not less than 0.15 and not greater than 3.5 did not exhibit surface defects such as anti phase boundaries and twin crystals.

[0084] As set forth above, the use of the method of manufacturing silicon carbide provided by the present invention yields a silicon carbide growth rate of 10 $\mu\text{m/hr}$ or greater and improves quality.

Table 1

fc2 (sccm)	fc2/fs (pc2/ps)	silicon carbide growth rate ($\mu\text{m/hr}$)
0.5	0.05	silicon precipitation
1	0.1	silicon precipitation
1.5	0.15	5
1.7	0.17	5
2	0.2	7
2.3	0.23	8
2.5	0.25	11
3	0.3	21
4	0.4	23
5	0.5	24
10	1	24
15	1.5	18
20	2	13
25	2.5	13
30	3	5
35	3.5	3
40	4	0.5
50	5	0
100	10	0
200	20	0

[0085] Although a cold wall type CVD device was employed in the present embodiment, the same effects can be achieved in the present embodiment using a hot wall type CVD device.

[0086] Further, although the silicon {001} plane was employed as substrate, the same rapid growth and crystal properties as in the present embodiment can be achieved using the silicon {111} plane, cubic silicon carbide {001} plane, cubic silicon carbide {111} plane, cubic silicon carbide $\{-1, -1, -1\}$ plane, hexagonal silicon carbide $\{1, 1, -2, 0\}$ plane, hexagonal silicon carbide $\{0, 0, 0, 1\}$ plane, hexagonal silicon carbide $\{0, 0, 0, -1\}$ plane, and hexagonal silicon carbide $\{1, -10, 0\}$ plane.

[0087] Although C_2H_2 was employed as the carbon source and SiH_2Cl_2 as the silicon source in the present embodiment, so long as the partial pressure ratio (flow rate ratio) of the carbon source to the silicon source is not less than one time and not more than ten times the attachment coefficient ratio, at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_4 , C_2H_6 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source, and at least one member selected from the group consisting of SiH_4 , Si_2H_6 , SiCl_4 , SiHCl_3 , $\text{Si}(\text{CH}_3)_4$, $\text{SiH}_2(\text{CH}_3)_2$, $\text{SiH}(\text{CH}_3)_3$, and $\text{Si}_2(\text{CH}_3)_6$ can be employed as the silicon source to achieve the effect of the present invention.

Embodiment 3

[0088] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of $1,300^\circ\text{C}$, and cubic silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of H_2 to a pressure of 60 mTorr during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiCl_4 and C_2H_5 . The ratio S_s/S_c of the attachment coefficients of SiCl_4 and C_2H_5 on the surface of the silicon carbide was 0.68.

[0089] The embodiment of the present invention will be described based on Fig. 7 below.

While continuously feeding SiCl_4 at a flow rate of 20 sccm, C_2H_5 was intermittently fed to grow silicon carbide. C_2H_5 was fed 1,000 times at intervals of 5 sec, each time lasting 5 sec. However, the flow rate f_c of C_2H_5 was treated as a parameter and f_c was varied from 0.5-200 sccm and the change in silicon carbide growth rate was observed ($f_{c1}=0$, that is, $p_{c1}=0$).

[0090] Table 2 shows the changes in growth rates of silicon carbide by f_{c2} . When f_{c2}/f_s (that is, p_{c2}/p_s) was S_s/S_c (0.68) or greater, the growth rate of silicon carbide exceeded $10 \mu\text{m/hr}$ and the effect of the present invention was marked. However, when f_{c2}/f_s (that is, p_{c2}/p_s) was less than S_s/S_c (0.68), not only did the growth rate of silicon carbide decrease, but silicon precipitated in the silicon carbide, precluding the effect of the present invention. Further, when

fc2/fs (that is, pc2/ps) exceeded 6.8, the level of adsorption of C_2H_5 on the substrate surface increased. Since adsorption of $SiCl_4$ was blocked, the growth rate of silicon carbide dropped precipitously, precluding the effect of the present invention.

[0091] Silicon carbide grown at an fc2/fs (that is, pc2/ps) of not less than 0.2 and not greater than 5 did not exhibit surface defects such as anti phase boundaries and twin crystals.

[0092] As set forth above, the use of the method of manufacturing silicon carbide provided by the present invention yields a silicon carbide growth rate of 10 $\mu m/hr$ or greater and improves quality.

Table 2

fc2 (sccm)	fc2/fs (pc2/ps)	silicon carbide growth rate ($\mu m/hr$)
0.5	0.025	silicon precipitation
1	0.05	silicon precipitation
1.5	0.075	silicon precipitation
1.7	0.085	silicon precipitation
2	0.1	1.2
2.3	0.115	1.5
2.5	0.125	1.5
3	0.15	1.5
4	0.2	2.1
5	0.25	3.8
10	0.5	6.7
15	0.75	22
20	1	71
25	1.25	67
30	1.5	65
35	1.75	65
40	2	61
50	2.5	61
100	5	52
200	10	0

[0093] Although a cold wall type CVD device was employed in the present embodiment, the same effects can be achieved in the present embodiment using a hot wall type CVD device.

[0094] Further, although the silicon {001} plane was employed as substrate, the same rapid growth and crystal properties as in the present embodiment can be achieved using the silicon {111} plane, cubic silicon carbide {001} plane, cubic silicon carbide {111} plane, cubic silicon carbide {-1,-1,-1} plane, hexagonal silicon carbide {1,1,-2,0} plane, hexagonal silicon carbide {0,0,0,1} plane, hexagonal silicon carbide {0,0,0,4} plane, and hexagonal silicon carbide {1,-10,0} plane.

[0095] Although C_2H_5 was employed as the carbon source and $SiCl_4$ as the silicon source in the present embodiment, so long as the partial pressure ratio (flow rate ratio) of the carbon source to the silicon source is not less than one time and not more than ten times the attachment coefficient ratio, at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_2 , C_2H_6 , C_2H_4 , C_2H_6 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source, and at least one member selected from the group consisting of SiH_4 , Si_2H_6 , SiH_2Cl_2 , $SiHCl_3$, $Si(CH_3)_4$, $SiH_2(CH_3)_2$, $SiH(CH_3)_3$, and $Si_2(CH_3)_6$ can be employed as the silicon source to achieve the effect of the present invention.

Embodiment 4

[0096] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of 1,200°C, and cubic silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of Ar to a pressure of 100 mTorr during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiH_2Cl_2 and C_2H_2 . The ratio Ss/Sc of the attachment coefficients of SiH_2Cl_2 and C_2H_2 on the surface of the silicon carbide was 0.25.

[0097] The embodiment of the present invention will be described based on Fig. 8 below.

While continuously feeding SiH_2Cl_2 , C_2H_2 was intermittently fed to grow silicon carbide. The C_2H_2 flow rate (fc2) was

a constant 10 sccm ($fc_1=0$, that is, $pc_1=0$). C_2H_2 was intermittently fed 1,000 times at intervals of 5 sec for 5 sec each time. However, the flow rate fs of SiH_2Cl_2 was treated as a parameter and fs was varied from 15 sccm to 200 sccm and the change in silicon carbide growth rate was observed.

[0098] Table 3 shows the changes in growth rates of silicon carbide by fs . When fc_2/fs (that is, pc_2/ps) was Ss/Sc (0.25) or greater, the growth rate of silicon carbide exceeded 10 $\mu m/hr$ and the effect of the present invention was apparent. However, when fc_2/fs (that is, pc_2/ps) was less than Ss/Sc (0.25), not only did the growth rate of silicon carbide decrease, but silicon precipitated in the silicon carbide, precluding the effect of the present invention. Further, when fc_2/fs (that is, pc_2/ps) exceeded 2.5, the level of adsorption of C_2H_2 on the substrate surface increased. Since adsorption of SiH_2Cl_2 was blocked, the growth rate of silicon carbide dropped precipitously, precluding the effect of the present invention.

[0099] Silicon carbide grown at an fc_2/fs (that is, pc_2/ps) of not less than 0.2 and not greater than 10 did not exhibit surface defects such as anti phase boundaries and twin crystals.

[0100] As set forth above, the use of the method of manufacturing silicon carbide provided by the present invention yields a silicon carbide growth rate of 10 $\mu m/hr$ or greater and improves quality.

Table 3

fc_2 (sccm)	fc_2/fs (pc_2/ps)	silicon carbide growth rate ($\mu m/hr$)
0.1	100	0
0.5	20	0
1	10	5
5	2	13
10	1	24
15	0.67	24
20	0.5	24
25	0.4	23
30	0.33	21
35	0.29	17
40	0.25	11
45	0.22	7
50	0.2	7
60	0.17	5
70	0.14	5
80	0.13	Silicon precipitation
90	0.11	Silicon precipitation
100	0.1	Silicon precipitation
150	0.067	Silicon precipitation
200	0.05	Silicon precipitation

[0101] Although a cold wall type CVD device was employed in the present embodiment, the same effects can be achieved in the present embodiment using a hot wall type CVD device.

[0102] Further, although the silicon {001} plane was employed as substrate, the same rapid growth and crystal properties as in the present embodiment can be achieved using the silicon {111} plane, cubic silicon carbide {001} plane, cubic silicon carbide {111} plane, cubic silicon carbide $\{-1,-1,-1\}$ plane, hexagonal silicon carbide $\{1,1,-2,0\}$ plane, hexagonal silicon carbide $\{0,0,0,1\}$ plane, hexagonal silicon carbide $\{0,0,0,-1\}$ plane, and hexagonal silicon carbide $\{1,-10,0\}$ plane.

[0103] Although C_2H_2 was employed as the carbon source and SiH_2Cl_2 as the silicon source in the present embodiment, so long as the partial pressure ratio (flow rate ratio) of the carbon source to the silicon source is not less than one time and not more than ten times the attachment coefficient ratio, at least one member selected from the group

consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_4 , C_2H_2 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source, and at least one member selected from the group consisting of SiH_4 , Si_2H_6 , SiCl_4 , SiHCl_3 , $\text{Si}(\text{CH}_3)_4$, $\text{SiH}_2(\text{CH}_3)_2$, $\text{SiH}(\text{CH}_3)_3$, and $\text{Si}_2(\text{CH}_3)_6$ can be employed as the silicon source to achieve the effect of the present invention.

5 Embodiment 5

[0104] Employing the {001} plane of a single-crystal silicon substrate as the single-crystal growth substrate, the substrate was heated to a temperature of $1,200^\circ\text{C}$, and cubic silicon carbide was epitaxially grown on the upper layer thereof. Using a cold wall type CVD device, the pressure was adjusted through the introduction of Ar to a pressure of 13.3 Pa (100 mTorr) during growth. The growth of silicon carbide on the silicon substrate was conducted by feeding feedstock gases in the form of SiH_2Cl_2 and C_2H_2 . The ratio S_s/S_c of the attachment coefficients of SiH_2Cl_2 and C_2H_2 on the surface of the silicon carbide was 0.25.

[0105] The embodiment of the present invention will be described based on Fig. 9 below.

While continuously feeding SiH_2Cl_2 , C_2H_2 was intermittently fed to grow silicon carbide. The SiH_2Cl_2 flow rate was a constant 10 sccm, and the C_2H_2 flow rate (f_{c2}) was a constant 10 sccm ($f_{c1}=0$, that is $p_{c1}=0$). C_2H_2 was repeatedly fed 1,000 times at intervals of 5 sec. However, the time during which C_2H_2 was fed each time, denoted as t_c , was taken as a parameter and varied from 0 sec to 60 sec, and the change in silicon carbide growth rate was observed.

[0106] Table 4 shows the changes in growth rates of silicon carbide based on t_c . When t_c was less than 0.1 sec, although the growth rate of silicon carbide exceeded $10 \mu\text{m/hr}$, the reaction between C_2H_2 and SiH_2Cl_2 was promoted in the vapor phase. Since the formation of silicon carbide was impeded at semicrystal positions, single crystal silicon carbide was not obtained. When t_c exceeded 30 sec, the growth time of silicon carbide lengthened and the adsorption of C_2H_2 on the substrate surface inhibited the adsorption of SiH_2Cl_2 , causing the growth rate of silicon carbide to drop below $10 \mu\text{m/hr}$. Accordingly, the effect of the present invention appears at a t_c of not less than 0.1 sec and not greater than 30 sec.

[0107] Silicon carbide grown at a t_c of not less than 0.1 sec and not more than 45 sec did not exhibit surface defects such as anti phase boundaries and twin crystals.

[0108] As set forth above, the use of the method of manufacturing silicon carbide provided by the present invention yields a silicon carbide growth rate of $10 \mu\text{m/hr}$ or greater and improves quality.

Table 4

t_c (sec)	Growth rate of silicon carbide ($\mu\text{m/hr}$)	Crystal properties
0	87	formation of silicon layer
0.05	85	polycrystal
0.1	70	single crystal
0.5	69	single crystal
1	62	single crystal
3	64	single crystal
5	61	single crystal
8	58	single crystal
10	61	single crystal
15	40	single crystal
20	35	single crystal
25	21	single crystal
30	11	single crystal
35	7	single crystal
40	7	single crystal
45	5	single crystal
50	0	
60	0	

[0109] Although a cold wall type CVD device was employed in the present embodiment, the same effects can be achieved in the present embodiment using a hot wall type CVD device.

[0110] Further, although the silicon {001} plane was employed as substrate, the same rapid growth and crystal properties as in the present embodiment can be achieved using the silicon {111} plane, cubic silicon carbide {001} plane, cubic silicon carbide {111} plane, cubic silicon carbide $\{-1,-1,-1\}$ plane, hexagonal silicon carbide $\{1,1,-2,0\}$ plane, hex-

agonal silicon carbide {0,0,0,1} plane, hexagonal silicon carbide {0,0,0,-1} plane, and hexagonal silicon carbide {1,-10,0} plane.

[0111] Although C_2H_2 was employed as the carbon source and SiH_2Cl_2 as the silicon source in the present embodiment, so long as the partial pressure ratio (flow rate ratio) of the carbon source to the silicon source is not less than one time and not more than ten times the attachment coefficient ratio, at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_4 , C_2H_2 , CCl_4 , CHF_3 , and CF_4 can be employed as the carbon source, and at least one member selected from the group consisting of SiH_4 , Si_2H_6 , $SiCl_4$, $SiHCl_3$, $Si(CH_3)_4$, $SiH_2(CH_3)_2$, $SiH(CH_3)_3$, and $Si_2(CH_3)_6$ can be employed as the silicon source to achieve the effect of the present invention.

Embodiment 6

[0112] Seed crystals were prepared from the silicon carbides obtained in Embodiments 1-5 and silicon carbide was grown by vapor growth epitaxy on the surfaces of these seed crystals.

[0113] While heating a seed crystal in the form of an SiC substrate based on the present invention to $1,200^\circ C$ under vacuum, 1 sccm of silane gas and 0.5 sccm of propane gas were introduced, and 1 slm of a dilution gas in the form of Ar was supplied. While maintaining the pressure in the reaction system at 13.3 Pa (100 mTorr), SiC was grown anew on the SiC seed crystal substrate. The seed crystal comprised cubic silicon carbide grown on a Si (001) substrate, and the silicon carbide that grew on the seed crystal was also cubic silicon carbide. The planar defect density of the seed crystal was $700/cm^2$, while that of the newly grown surface decreased to $30/cm^2$. Thus, it was possible to obtain extremely high quality silicon carbide of large (15.24 cm (6 inch)) bore.

[0114] In addition to the above-described vapor phase epitaxy, other methods such as sublimation recrystallization and liquid deposition can be employed to form silicon carbide on seed crystal.

Embodiment 7

[0115] The silicon carbide obtained in Embodiments 1-5 can be employed as seed crystal, upon which diamond, gallium nitride (GaN), or diamond and gallium nitride may be formed to obtain composite materials comprised of silicon carbide and diamond, composite materials comprised of silicon carbide and gallium nitride, and composite materials comprised of silicon carbide, diamond, and gallium nitride.

[0116] A seed crystal of cubic silicon carbide grown on an Si (001) substrate and prepared based on the present invention was placed in a vacuum chamber and heated to $500^\circ C$. Propane gas was then introduced into the vacuum chamber and the gas evacuation system was adjusted to generate a pressure within the chamber of 1.33 Pa (10 mTorr). Next, a 13.56 MHz high-frequency (200 W) was applied between the seed crystal and a flat electrode facing the seed crystal to form a plasma. Carbon decomposing due to the plasma was deposited on the seed crystal and kept in the proper crystal position, forming diamond on the seed crystal. The crystal orientation of the diamond surface was the (001) plane, as was that of the seed crystal, and the planar defect density decreased to $120/cm^2$. Thus, it was possible to obtain extremely high quality diamond with a large (15.24 cm (6 inch)) bore.

[0117] Gallium nitride was also formed on a seed crystal in the following manner.

[0118] A substrate (seed crystal) of silicon carbide obtained by the manufacturing method of the present invention was placed in a vacuum chamber and heated to $1,040^\circ C$. Next, 10 slm of ammonia and 0.5 sccm of trimethylgallium were introduced into the reaction vessel, and while the gases decomposed over the seed crystal, GaN formed at the proper crystal position. The GaN that formed was, like the seed crystal, a cubic crystal the surface of which was the (001) plane. The planar defect density was $700/cm^2$, identical to the seed crystal. Thus, it was possible to obtain extremely high quality GaN of large 15.24 (6 inch) bore.

[0119] Since the crystal defects of silicon carbide employed as seed crystal are suppressed and various materials can be grown and formed on such seed crystals, it is possible to obtain high-quality silicon carbide materials and composite materials.

[0120] Further, gold and nickel electrodes were formed by the usual methods on a composite material consisting of diamond formed on the above-described silicon carbide to prepare Schottky barrier diodes.

[0121] Blue light emitting diodes were obtained using a composite material consisting of gallium nitride formed on the above-described silicon carbide.

[0122] Since a composite material formed using seed crystal in the form of silicon carbide with no crystal defects is employed in the Schottky barrier diodes and blue light emitting diodes, good characteristics can be achieved in semiconductor elements.

[0123] Thus, based on the present invention, it is possible to manufacture high-quality silicon carbide affording good ease of production since the rate of growth of silicon carbide can be increased without a corresponding increase in crystal defects.

[0124] Further, based on the present invention, silicon carbide and composite materials can be obtained in which

crystal defects are suppressed.

Claims

1. A method of manufacturing silicon carbide by forming silicon carbide on a substrate surface from an atmosphere containing a silicon carbide feedstock gas, **characterized in that:**
said silicon carbide feedstock gas comprises at least a silicon source gas and a carbon source gas;
the partial pressure p_s of said silicon source gas in said atmosphere is constant (with $p_s > 0$), the partial pressure of said carbon source gas in said atmosphere consists of a state p_{c1} and a state p_{c2}
(where p_{c1} and p_{c2} denote partial pressures of said carbon source gas, $p_{c1} > p_{c2}$, and the partial pressure ratio (p_{c1}/p_s) falls within a range of 1-10 times the attachment coefficient ratio (S_s/S_c), the partial pressure ratio (p_{c2}/p_s) falls within a range of less than one time the attachment coefficient ratio (S_s/S_c)
(where S_s denotes the attachment coefficient of silicon source gas to the silicon carbide substrate at the substrate temperature during formation of said silicon carbide, and S_c denotes the attachment coefficient of carbon source gas to the silicon carbide substrate at the substrate temperature during the forming of said silicon carbide))
that are repeated in alternating fashion (referred to as condition 1 below); or
the partial pressure p_c of said carbon source gas in said atmosphere is constant (with $p_c > 0$), the partial pressure of said silicon source gas in said atmosphere consists of a state p_{s1} and a state p_{s2}
(where p_{s1} and p_{s2} denote partial pressures of said silicon source gas, $p_{s1} < p_{s2}$, and the partial pressure ratio (p_c/p_{s1}) falls within a range of 1-10 times the attachment coefficient ratio (S_s/S_c), the partial pressure ratio (p_c/p_{s2}) falls within a range of less than one time the attachment coefficient ratio (S_s/S_c)
(where S_s denotes the attachment coefficient of silicon source gas to the silicon carbide substrate at the substrate temperature during formation of said silicon carbide, and S_c denotes the attachment coefficient of carbon source gas to the silicon carbide substrate at the substrate temperature during the forming of said silicon carbide))
that are repeated in alternating fashion (referred to as condition 2 below).
2. The manufacturing method of claim 1 wherein in condition 1, p_{c1} and p_{c2} each continue for a prescribed period, and in condition 2, p_{s1} and p_{s2} each continue for a prescribed period.
3. The manufacturing method of claim 1 or 2 wherein silicon carbide is formed on a substrate the temperature of which is not less than 900°C.
4. The manufacturing method of any of claims 1-3 wherein said silicon source gas is at least one member selected from the group consisting of SiH_4 , Si_2H_6 , $SiCl_4$, $SiHCl_3$, SiH_2Cl_2 , $Si(CH_3)_4$, $SiH_2(CH_3)_2$, $SiH(CH_3)_3$, and $Si_2(CH_3)_6$, and/or said carbon source gas is at least one member selected from the group consisting of CH_4 , C_3H_8 , C_2H_5 , C_2H_6 , C_2H_2 , C_2H_4 , CCl_4 , CHF_3 , and CF_4 .
5. The manufacturing method of any of claims 1-4 wherein p_{c2} or p_{s1} is essentially 0.
6. The manufacturing method of any of claims 1-5 wherein p_{c2} is essentially 0, the time during which the partial pressure of the carbon source gas is set to p_{c1} is 0.1-30 seconds, and the time during which the partial pressure of the carbon source gas is set to p_{c2} is 0.1-30 seconds.
7. A method of manufacturing silicon carbide **characterized in that** the silicon carbide manufactured in any of claims 1-6 is employed as seed crystal and **in that** silicon carbide is formed on said seed crystal by vapor phase epitaxy, sublimation recrystallization, or liquid deposition.
8. The manufacturing method of claim 7 wherein silicon carbide blocks 10.16-15.24 cm (4-6 inches) in bore are formed by vapor phase epitaxy, sublimation recrystallization, or liquid deposition.
9. A silicon carbide block **characterized by** having a bore of 10.16 - 15.24 cm (4-6 inches).
10. The silicon carbide block of claim 9 wherein the planar defect density is not more than $10^3/cm^2$.
11. A semiconductor element employing as substrate the silicon carbide block described in claim 9 or 10.

EP 1 160 361 A1

12. A method of manufacturing composite materials **characterized in that** silicon carbide manufactured by the method of any of claims 1-6 is employed as seed crystal and diamond and/or gallium nitride is formed on said seed crystal.

5

10

15

20

25

30

35

40

45

50

55

Fig. 1

Condition 1




Fig. 2

Condition 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11





Fig.12



Change over time (relative value) of
number of molecules desorbed from
substrate as measured by quadrupole
mass spectrometry



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 3260

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 040 610 A (SZEKELY ANDREW GEZA) 9 August 1977 (1977-08-09) * column 3, line 28 - column 4, line 30 *	9	C30B25/02 C30B29/36 C30B25/00
A	YAGI K ET AL: "3C-SiC growth by alternate supply of SiH ₂ Cl ₂ and C ₂ H ₂ " JOURNAL OF CRYSTAL GROWTH, NORTH-HOLLAND PUBLISHING CO. AMSTERDAM, NL, vol. 174, no. 1-4, 1 April 1997 (1997-04-01), pages 653-657, XP004083864 ISSN: 0022-0248 * the whole document *	1-12	
A	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 06, 30 June 1997 (1997-06-30) & JP 09 052798 A (HOYA CORP), 25 February 1997 (1997-02-25) * abstract *	1	
A	US 5 937 316 A (INABA TAKESHI ET AL) 10 August 1999 (1999-08-10) * claims 10-14 *	1, 3, 4	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C30B
A	YAKIMOVA R ET AL: "Current status and advances in the growth of SiC" DIAMOND AND RELATED MATERIALS, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 9, no. 3-6, April 2000 (2000-04), pages 432-438, XP004199791 ISSN: 0925-9635		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 9 October 2001	Examiner Cook, S
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EP 01 11 3260 (1999-08-10)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 3260

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

09-10-2001

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 4040610	A	09-08-1977	KR	8100403 A	29-04-1981
			AR	216773 A1	31-01-1980
			AT	364171 B	25-09-1981
			AT	588777 A	15-02-1981
			AU	509438 B2	15-05-1980
			AU	2792877 A	21-06-1979
			BE	857837 A1	16-02-1978
			BR	7705375 A	13-03-1979
			CA	1082456 A1	29-07-1980
			CH	624478 A5	31-07-1981
			CS	207478 B1	31-07-1981
			DD	132449 A5	27-09-1978
			DE	2736793 A1	23-02-1978
			ES	461601 A1	16-06-1978
			ES	464220 A1	01-07-1978
			FR	2362213 A1	17-03-1978
			GB	1590063 A	28-05-1981
			GR	62638 A1	15-05-1979
			HU	177769 B	28-12-1981
			IE	45466 B1	08-09-1982
			IN	149328 A1	24-10-1981
			IT	1079449 B	13-05-1985
			JP	1093305 C	16-04-1982
			JP	53023806 A	04-03-1978
			JP	56031849 B	24-07-1981
			MX	146745 A	05-08-1982
			NL	7708989 A ,B,	20-02-1978
			NO	772845 A ,B,	17-02-1978
			NZ	184919 A	26-08-1980
			PL	200298 A1	10-04-1978
			RO	75233 A1	30-04-1981
			SE	428500 B	04-07-1983
			SE	7709192 A	17-02-1978
			YU	196377 A1	31-10-1982
			ZA	7704575 A	28-06-1978

JP 09052798	A	25-02-1997	NONE		

US 5937316	A	10-08-1999	JP	10012563 A	16-01-1998

EPO FORM P449

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82